

1. A decorative item comprising:

at least one hard coating disposed on a surface of the hardened layer of the basis material.

3. The decorative item as claimed in claim 1, wherein  
15 the basis material is constituted of stainless steel,  
titanium or a titanium alloy.

4. The decorative item as claimed in any of claims 1 to 3, wherein the hard coating and the basis material at its surface exhibit respective tones which are different from each other.

5. The decorative item as claimed in any of claims 1 to 4, wherein the hard coating has a surface hardness greater than that of the basis material.

6. The decorative item as claimed in any of claims 1 to 5, wherein the hard coating is constituted of a nitride, carbide, oxide, nitrido-carbide or nitrido-carbido-oxide of an element belonging to Group 4a, 5a or 6a of the periodic table.

7. The decorative item as claimed in any of claims 1 to 5, wherein the hard coating is a hard coating of carbon.

8. The decorative item as claimed in claim 7, further comprising an intermediate layer disposed between the hard coating of carbon and a surface of the hardened layer of the basis material.

9. The decorative item as claimed in claim 8, wherein the intermediate layer comprises a lower layer of Ti or Cr disposed on the hardened layer surface of the basis material and an upper layer of Si or Ge disposed on a surface of the lower layer.

10. The decorative item as claimed in any of claims 1 to 7, wherein at least two hard coatings are formed on the hardened layer surface of the basis material.

Sub A5  
Cont

00831327.050701

Sub B2

Sub A6

11. The decorative item as claimed in any of claims 1 to 7, wherein at least two hard coatings are laminated on the hardened layer surface of the basis material.

12. The decorative item as claimed in any of claims 1 to 10, wherein the hard coating is disposed on portion of the hardened layer surface of the basis material.

13. The decorative item as claimed in any of claims 1 to 12, further comprising a gold alloy coating disposed on a surface of the hard coating.

14. The decorative item as claimed in claim 13, wherein the gold alloy coating is constituted of an alloy of gold and at least one metal selected from the group consisting of Al, Si, V, Cr, Ti, Fe, Co, Ni, Cu, Zn, Ge, Y, Zr, Nb, Mo, Ru, Rh, Pd, Ag, Cd, In, Sn, Hf, Ta, W, Ir and Pt.

15. The decorative item as claimed in any of claims 1 to 14, which is an exterior part of timepiece.

16. A process for producing a decorative item, comprising the steps of:

Sub A1e  
Cont

Sub A17

Sub B14

FO/050 22700

providing a basis material of stainless steel having a hardened layer extending from a surface thereof to an arbitrary depth wherein a solute atom is diffused so as to form a solid solution; and forming at least one hard coating on a surface of the hardened layer of the basis material.

17. The process as claimed in claim 16, wherein the solute atom is at least one atom selected from the group consisting of carbon, nitrogen and oxygen atoms.

18. The process as claimed in claim 16 or 17, wherein the decorative item is an exterior part of timepiece.

19. An exterior part of timepiece, comprising a stainless steel having at its surface a carburized layer wherein carbon is diffused so as to form a solid solution, wherein the carburized layer has a polished surface whose Vickers hardness (HV) is 500 or more.

20. The exterior part of timepiece as claimed in claim 19, wherein the polished surface is specular.

09831327-050701

Sub B7  
Cont

Sub A8

Sub B5

21. An exterior part of timepiece, comprising a stainless steel having at its surface a carburized layer wherein carbon is diffused so as to form a solid solution,

wherein the carburized layer has a machined surface.

22. The exterior part of timepiece as claimed in claim 21, wherein the machined surface has a Vickers hardness  
10 (HV) of 500 or more.

23. The exterior part of timepiece as claimed in claim 21 or 22, which is one produced by machining a surface of an exterior part of timepiece and thereafter  
15 carburizing the machined surface.

24. A wristwatch band comprising a plurality of band pieces of stainless steel connected to each other,

each of the band pieces having at its surface a  
20 carburized layer wherein carbon is diffused so as to form a solid solution,

wherein the carburized layer has a polished surface whose Vickers hardness (HV) is 500 or more.

00831327-050701

Sub B6

Sub A9

Sub B7

25. A wristwatch band comprising a plurality of band pieces of stainless steel connected to each other,

each of the band pieces having at its surface a carburized layer wherein carbon is diffused so as to form a solid solution,

wherein the carburized layer has a machined surface.

26. The wristwatch band as claimed in claim 24 or 25,

wherein the band pieces are connected to each other by means of connecting parts of stainless steel,

each of the connecting parts having at at least portion of its surface a carburized layer wherein carbon is diffused so as to form a solid solution.

27. The wristwatch band as claimed in claim 24 or 25, produced by connecting the band pieces to each other by means of connecting parts, carburizing the band pieces and the connecting parts, and thereafter polishing surfaces of the band pieces.

28. The wristwatch band as claimed in claim 27, which further comprises connecting parts having no carburized layer.

Sub B7  
Cont

09831327-050704

Sub A10  
15

29. A process for producing a wristwatch band,  
comprising the steps of:

connecting a plurality of band pieces of stainless  
steel to each other by means of a plurality of

5 connecting parts of stainless steel;

fluorinating the band pieces and the connecting  
parts in a fluorogas atmosphere at 400 to 500°C;

gas carburizing the fluorinated band pieces and  
connecting parts in a carburizing gas atmosphere  
10 containing carbon monoxide at 400 to 500°C;

pickling the carburized band pieces and connecting  
parts, followed by rinsing; and

subjecting surfaces of the band pieces to barrel  
polishing.

15

30. The process as claimed in claim 29, which further  
comprises buffing the band piece surfaces having  
undergone barrel polishing.

20 31. The process as claimed in claim 29 or 30, which  
further comprises machining surfaces of the band pieces  
connected by means of the connecting parts prior to the  
fluorination to obtain a wristwatch band having  
machined surfaces.

Sub All

00634327.050704

32. A process for producing a wristwatch band,  
comprising the steps of:

fluorinating a plurality of band pieces of  
stainless steel and a plurality of connecting parts of  
5 stainless steel in a fluorogas atmosphere at 250 to  
600°C;

gas carburizing the fluorinated band pieces and  
connecting parts in a carburizing gas atmosphere  
containing carbon monoxide at 400 to 500°C;

10 pickling the carburized band pieces and connecting  
parts, followed by rinsing;

subjecting surfaces of the band pieces to barrel  
polishing; and

connecting the band pieces by means of the  
15 connecting parts.

33. The process as claimed in claim 32, which further  
comprises buffing the band piece surfaces having  
undergone barrel polishing.

20

34. The process as claimed in claim 32 or 33, which  
further comprises machining surfaces of the plurality  
of band pieces prior to the fluorination to obtain a  
wristwatch band having machined surfaces.

09831327-050704

Sub A12



35. A process for producing an exterior part of timepiece other than a wristwatch band, comprising the steps of:

connecting a plurality of pieces of stainless steel to each other by means of a plurality of connecting parts of stainless steel to obtain a base material for a timepiece exterior part of stainless steel other than a wristwatch band;

fluorinating the base material in a fluorogas atmosphere at 250 to 600°C;

gas carburizing the fluorinated base material in a carburizing gas atmosphere containing carbon monoxide at 400 to 500°C;

pickling the carburized base material, followed by rinsing; and

subjecting surfaces of the base material to barrel polishing.

36. The process as claimed in claim 35, which further comprises buffing the base material surfaces having undergone barrel polishing.

37. The process as claimed in claim 35 or 36, which further comprises machining surfaces of the base material prior to the fluorination to obtain an

09831327-050701

Sub A13  
28

[illegible]

10

15

20

Sub A14

42. The exterior part of timepiece as claimed in any of claims 38 to 41, wherein the hardened layer extends from a surface of the deformed layer to a depth of 5 to 50  $\mu\text{m}$ .

43. The exterior part of timepiece as claimed in any of claims 38 to 42, wherein the solute atom is at least one atom selected from the group consisting of carbon, nitrogen and oxygen atoms.

44. The exterior part of timepiece as claimed in any of claims 38 to 43, wherein the hardened layer has a specular surface whose Vickers hardness (HV) is 500 or greater.

45. A process for producing an exterior part of timepiece constituted of stainless steel, comprising the steps of:

applying a physical external force to a surface of stainless steel so as for at least the stainless steel surface to have a deformed layer containing a fibrous structure wherein metal crystal grains are deformed so as to be fibrous; and

dissolving a solute atom in a surface of the deformed layer so as to form a solid solution therein,

2000-05-07  
 05:07:01  
 Sub Amp  
 Cont

thereby effecting such a hardening that a hardened layer is formed.

46. The process as claimed in claim 45, wherein the  
5 deformed layer is formed by application to the stainless steel surface of a physical external force capable of drawing the stainless steel surface substantially unidirectionally.

10 47. The process as claimed in claim 45 or 46, wherein the deformed layer is formed by subjecting the stainless steel surface to at least one of polishing and cutting operations whereby a physical external force capable of drawing the stainless steel surface  
15 substantially unidirectionally is applied to the stainless steel surface.

20 48. The process as claimed in any of claims 45 to 47, wherein the deformed layer is formed by subjecting the stainless steel surface to at least one of cutting and grinding operations to form a face of desired shape, and

polishing the face of desired shape to form the deformed layer.

09831327-050701

Sub A15

49. The process as claimed in any of claims 45 to 47, wherein the stainless steel surface is subjected to grinding operation to form not only a face of desired shape but also the deformed layer.

5

50. The process as claimed in claim 48 or 49, wherein the face of desired shape is substantially flat.

10

51. The process as claimed in claim 48 or 49, wherein the face of desired shape is curved.

15

52. The process as claimed in any of claims 45 to 51, wherein the deformed layer is so formed as to extend from the stainless steel surface to a depth of 2 to 100  $\mu\text{m}$ .

20

53. The process as claimed in any of claims 45 to 52, wherein the hardened layer is so formed as to extend from a surface of the deformed layer to a depth of 5 to 50  $\mu\text{m}$ .

25

54. The process as claimed in any of claims 45 to 53, wherein the solute atom is at least one atom selected from the group consisting of carbon, nitrogen and oxygen atoms.

FOI 0950 2327 050701

Sub A15  
Cont

Sub A15  
Cont

Add  
A16

Add Ba